

L.P. Bader & Co. GmbH  
Neckartal 140    D-78628 Rottweil  
☒ Postfach 1137    D-78611 Rottweil

Telefon: + 49 (0)7 41-9 42 52-0  
Telefax: + 49 (0)7 41-9 42 52-50

E-Mail: [service@lubaprint.de](mailto:service@lubaprint.de)  
Internet: [www.lubaprint.de](http://www.lubaprint.de)

## LUBA-print Wax Dispersion 490/C (ND)

### Application field:

- Solvent-based lacquers
- Can-and coil-coatings
- Epoxidphenol-systems:  
improve the slip property for high gloss systems.

### Processing information:

2 - 4 % of this wax dispersion to be added to the lacquer while stirring

### Technical data:

### Unit:

### Method:

Solid:	min:	9,0	%	Sartorius MA 100 infrared drier
	max:	11,0	%	
		Polyethylene-Wax/ microcryst. Wax		
Drop point:	min:	99	°C	DIN ISO 2176 (solid wax)
	max:	107	°C	
Solvent:		Solvent Naphtha ND Boiling Range 180-215 °C		
Particle size 50%:	min:	2,5	µm	Picture-Particle-Analyzing-System
	max:	3,5	µm	
Fineness 98% <:		7,0	µm	Picture-Particle-Analyzing-System
Density:	min:	0,88	g/ccm	Pyknometer DIN EN ISO 2811-1
	max:	0,90	g/ccm	
Viscosity:	min:	8	mPa.s	Rheolab MC1 DIN 53019 1.291s-1
	max:	14	mPa.s	

### Storage:

In original closed containers lasting at least 12 months at temperatures between 5-35°C.  
Stir well before use!

The above mentioned information is derived from our quality checks. It does not relieve the purchaser from examining the product delivery and gives no assurance of suitability of the product for any particular purpose.