

L.P. Bader & Co. GmbH
Neckartal 140 D-78628 Rottweil
☒ Postfach 1137 D-78611 Rottweil

Telefon: + 49 (0)7 41-9 42 52-0
Telefax: + 49 (0)7 41-9 42 52-50

E-Mail: service@lubaprint.de
Internet: www.lubaprint.de

LUBA-print Wax Dispersion 254/A-PM (ND)

Application field:

- Metal paints
- Can-and coil-coating:
improve slip property and mar resistance.

Processing information:

2 - 6 % of this wax dispersion to be added to the paint while stirring

Technical data:

Unit:

Method:

Solid:	min:	9,0	%	Sartorius MA 100 infrared drier
	max:	11,0	%	
		Carnauba-Wax		
Melting range:	min:	87	°C	DSC (solid wax)
	max:	93	°C	
Solvent:		Solvent Naphtha ND (Boiling Range 180-215 °C) / Propan-2-ol in a ratio 60:30		
Particle size 50%:	min:	2,0	µm	Picture-Particle-Analyzing-System
	max:	3,0	µm	
Fineness 98% <:		7,0	µm	Picture-Particle-Analyzing-System
Density:	min:	0,85	g/ccm	Pyknometer DIN EN ISO 2811-1
	max:	0,87	g/ccm	
Viscosity:	min:	10	mPa.s	Rheolab MC1 DIN 53019 1.291s-1
	max:	20	mPa.s	

Storage:

In original closed containers lasting at least 12 months at temperatures between 5-35°C.
Stir well before use!

The above mentioned information is derived from our quality checks. It does not relieve the purchaser from examining the product delivery and gives no assurance of suitability of the product for any particular purpose.