

L.P. Bader & Co. GmbH
 Neckartal 140 D-78628 Rottweil
 ☒ Postfach 1137 D-78611 Rottweil

Telefon: + 49 (0)7 41-9 42 52-0
 Telefax: + 49 (0)7 41-9 42 52-50

E-Mail: service@lubaprint.de
 Internet: www.lubaprint.de

LUBA-print Wax Dispersion VP 601/B

Application field:

Solvent-based Can-Coating:
 to improve slip property and scratch resistance.

Processing information:

2-6 % of this wax dispersion to be added to the lacquer while stirring.

<u>Technical data:</u>	<u>Unit:</u>	<u>Method:</u>
Solid:	min: 24,0 % max: 26,0 %	Sartorius MA 100 infrared drier
	Wax-combination	
Melting range:	min: 123 °C max: 133 °C	DSC (solid wax)
Solvent:	Solvent naphtha (Boiling range: 180-215°C) / Butyl glycol in a ratio 50:25	
Particle size 50%:	min: 4,0 µm max: 6,0 µm	Picture-Particle-Analyzing-System
Fineness 98% <:	12,0 µm	Picture-Particle-Analyzing-System
Density:	min: 0,89 g/ccm max: 0,91 g/ccm	Pyknometer DIN EN ISO 2811-1
Viscosity:	typ.: 50 mPa.s	Rheolab MC1 DIN 53019 1.291s-1

Experimental product: Temporary data, final limits can be given after 5 produced batches.

Storage:

In original closed containers lasting at least 6 months at temperatures between 5-35°C.

Stir well before use!

The above mentioned information is derived from our quality checks. It does not relieve the purchaser from examining the product delivery and gives no assurance of suitability of the product for any particular purpose.