

L.P. Bader & Co. GmbH
Neckartal 140 D-78628 Rottweil
☒ Postfach 1137 D-78611 Rottweil

Telefon: + 49 (0)7 41-9 42 52-0
Telefax: + 49 (0)7 41-9 42 52-50

E-Mail: service@lubaprint.de
Internet: www.lubaprint.de

LUBA-print Wax Dispersion VP 459/Z

Application field:

Waterproofing of surfaces, to improve the depth of colour from marbling effects and smoothing technique (stucco).

Processing information:

A thin coating should be applied and polished afterwards. The polish ability and the pasty appearance depend on the ambient temperatures. When using lime stucco it is necessary to test the compatibility to avoid changes in colour.

Opened product should be processed at once.

Technical data:

Unit:

Method:

| | | | |
|------------|------|---|---------------------------------|
| Solid: | min: | 30,0 % | Sartorius MA 100 infrared drier |
| | max: | 32,0 % | |
| Solvent: | | Paraffin combination | |
| | | Dearomatized Hydrocarbon (Boiling Range: > 250°C- non VOC) | |
| | | Isoparaffinic Hydrocarbon (Boiling Range: 153-178°C) | |
| | | Water | |
| | | in a ratio 24 : 23,5 : 19 | |
| Density: | min: | 0,79 g/ccm | Pyknometer DIN EN ISO 2811-1 |
| | max: | 0,81 g/ccm | |
| Viscosity: | | pasty | |

Storage:

In original closed containers lasting at least 6 months at temperatures between 5-35°C.

The above mentioned information is derived from our quality checks. It does not relieve the purchaser from examining the product delivery and gives no assurance of suitability of the product for any particular purpose.