

L.P. Bader & Co. GmbH  
 Neckartal 140 D-78628 Rottweil  
 ☒ Postfach 1137 D-78611 Rottweil

Telefon: + 49 (0)7 41-9 42 52-0  
 Telefax: + 49 (0)7 41-9 42 52-50

E-Mail: [service@lubaprint.de](mailto:service@lubaprint.de)  
 Internet: [www.lubaprint.de](http://www.lubaprint.de)

## LUBA-print Wax Dispersion VP 103/M

### Application field:

Wood lacquers,  
 to improve scratch resistance and sandability.

### Processing information:

2 - 6 % of this wax dispersion to be added to the lacquer while stirring

### Technical data:

### Unit:

### Method:

Solid:	min:	24,0 %	Sartorius MA 100 infrared drier
	max:	26,0 %	
		Calcium stearate	
		Butyl acetate	
Solvent:			Picture-Particle-Analyzing-System
	Particle size 50%:	min: 4,0 µm	
	max:	5,0 µm	
Fineness 98% <:		10,0 µm	Picture-Particle-Analyzing-System
Density:	min:	0,89 g/ccm	Pyknometer DIN EN ISO 2811-1
	max:	0,91 g/ccm	
Viscosity:	typ.:	45 mPa.s	Rheolab MC1 DIN 53019 1.291s-1

Experimental product: Temporary data, final limits can be given after 5 produced batches.

### Storage:

In original closed containers lasting at least 6 months at temperatures between 5-35°C.

Stir well before use!

The above mentioned information is derived from our quality checks. It does not relieve the purchaser from examining the product delivery and gives no assurance of suitability of the product for any particular purpose.