

L.P. Bader & Co. GmbH
 Neckartal 140 D-78628 Rottweil
 Postfach 1137 D-78611 Rottweil

Telefon: + 49 (0)7 41-9 42 52-0
 Telefax: + 49 (0)7 41-9 42 52-50

E-Mail: service@lubaprint.de
 Internet: www.lubaprint.de

LUBA-print Wax Dispersion 346/F

Application field:

Lacquers and glaze:
 to reduce settling property.

Processing information:

base - coat: approximately 10 % to be added to the base coat while stirring.
 Stir well before use.
 EVA-copolymer dispersions have the tendency to build up agglomerates.

Technical data:

Unit:

Method:

Solid:	min:	14,0 %	Sartorius MA 100 infrared drier
	max:	16,0 %	
Melting range:		EVA - Copolymer	DSC (solid wax)
	min:	88 °C	
Solvent:	max:	98 °C	Pyknometer DIN EN ISO 2811-1
		Butyl acetate/ Dearomatized Hydrocarbon (Boiling Range 140-170°C)/ Isobutanol in a ratio 48:29:9	
Density:	min:	0,82 g/ccm	Rheolab MC1 DIN 53019 1.291s-1
	max:	0,84 g/ccm	
Viscosity:	min:	10 mPa.s	
	max:	50 mPa.s	

Storage:

In original closed containers lasting at least 12 months at temperatures between 5-35°C.

The above mentioned information is derived from our quality checks. It does not relieve the purchaser from examining the product delivery and gives no assurance of suitability of the product for any particular purpose.