

L.P. Bader & Co. GmbH
Neckartal 140 ▲ D-78628 Rottweil
☒ Postfach 1137 ▲ D-78611 Rottweil

Telefon: + 49 (0)7 41-9 42 52-0
Telefax: + 49 (0)7 41-9 42 52-50

E-Mail: service@lubaprint.de
Internet: www.lubaprint.de

LUBA-print Wax Dispersion 459

Application field:

Solvent- based lacquers:
to improve hydrophoby and antiblocking

Processing information:

3-10 % of this wax dispersion to be added to the lacquer while stirring

Technical data:

Unit:

Method:

Solid:	min:	18,5 %	Sartorius MA 100 infrared drier
	max:	20,5 %	
		Paraffine combination	
Drop point:	min:	97 °C	DIN ISO 2176 (solid wax)
	max:	105 °C	
Solvent:		Isoparaffinic Hydrocarbon	
		Boiling Range 153-178°C	
Density:	min:	0,76 g/ccm	Pyknometer DIN EN ISO 2811-1
	max:	0,78 g/ccm	
Viscosity:	min:	8 mPa.s	Rheolab MC1 DIN 53019 1.291s-1
	max:	35 mPa.s	

Storage:

In original closed containers lasting at least 12 months at temperatures between 5-35°C.
Stir well before use!

The above mentioned information is derived from our quality checks. It does not relieve the purchaser from examining the product delivery and gives no assurance of suitability of the product for any particular purpose.