

LUBA-print Wax Dispersion 582/E

Application field:

Wood-Coatings
to improve metalmarking and slip property.

Processing information:

3 - 10 % of this wax dispersion to be added to the laquer while stirring.
To be added at laquer-processing as soon as possible to ensure an optimal distribution.

Technical data:

Unit:

Method:

Solid:	min:	11,0 %	Sartorius MA 100 infrared drier
	max:	13,0 %	
Drop point:	min:	109 °C	DIN ISO 2176 (solid wax)
	max:	117 °C	
Solvent:		Butyl acetate	
Density:	min:	0,87 g/ccm	Pyknometer DIN EN ISO 2811-1
	max:	0,89 g/ccm	
Viscosity:	min:	2 mPa.s	Rheolab MC1 DIN 53019 1.291s-1
	max:	30 mPa.s	

Storage:

In original closed containers lasting at least 12 months at temperatures between 5-35°C.

Stir well before use!

The above mentioned information is derived from our quality checks. It does not relieve the purchaser from examining the product delivery and gives no assurance of suitability of the product for any particular purpose.