

L.P. Bader & Co. GmbH
Neckartal 140 D-78628 Rottweil
☒ Postfach 1137 D-78611 Rottweil

Telefon: + 49 (0)7 41-9 42 52-0
Telefax: + 49 (0)7 41-9 42 52-50

E-Mail: service@lubaprint.de
Internet: www.lubaprint.de

LUBA-print Wax Dispersion VP 709/P

Application field:

UV- lacquers,
to improve slip while maintaining gloss.

Processing information:

2 - 6 % of this wax dispersion to be added to the lacquer while stirring.

Technical data:

Unit:

Method:

Solid:	min:	17,0 %		after solvent extraktion
	max:	19,0 %		
		Wax Combination		
Drop point:	min:	71 °C		DIN 51801 (solid wax)
	max:	82 °C		
Solvent:		Tripropylenglycoldiacrylate (TPGDA) / Oligotriacrylate (OTA 480) in a ratio 52:21		
Particle size 50%:	min:	4,0 µm		Picture-Particle-Analyzing-System
	max:	6,0 µm		
Fineness 98% <:		10,0 µm		Picture-Particle-Analyzing-System
Density:	min:	0,88 g/ccm		Pyknometer DIN EN ISO 2811-1
	max:	0,90 g/ccm		
Viscosity:	typ.:	140 mPa.s		Rheolab MC1 DIN 53019 1.291s-1

Experimental product: Temporary data, final limits can be given after 4 produced batches.

Storage:

In original closed containers lasting at least 6 months at temperatures between 5-35°C.
Stir well before use!

The above mentioned information is derived from our quality checks. It does not relieve the purchaser from examining the product delivery and gives no assurance of suitability of the product for any particular purpose.