

L.P. Bader & Co. GmbH  
Neckartal 140    D-78628 Rottweil  
☒ Postfach 1137    D-78611 Rottweil

Telefon: + 49 (0)7 41-9 42 52-0  
Telefax: + 49 (0)7 41-9 42 52-50

E-Mail: [service@lubaprint.de](mailto:service@lubaprint.de)  
Internet: [www.lubaprint.de](http://www.lubaprint.de)

## LUBA-print Wax Dispersion VP 644/B

### Application field:

Solvent based,  
to improve the water resistance of soft wood, antique wax effect

### Processing information:

The wax dispersion is applied directly on the wood, with additional polishing

### Technical data:

### Unit:

### Method:

Solid:	min:	24,0 %	Sartorius MA 100 infrared drier
	max:	26,0 %	
		Natural-Wax	
Melting range:	min:	55 °C	DSC (solid wax)
	max:	65 °C	
Solvent:		Isoparaffinic Hydrocarbons	
Density:	min:	0,76 g/ccm	Pyknometer DIN EN ISO 2811-1
	max:	0,78 g/ccm	
Viscosity:	typ.:	pasty	

Experimental product: Temporary data, final limits can be given after 4 produced batches.

fineness: measurement not applicable

### Storage:

In original closed containers lasting at least 6 months at temperatures between 5-35°C.  
Stir well before use!

The above mentioned information is derived from our quality checks. It does not relieve the purchaser from examining the product delivery and gives no assurance of suitability of the product for any particular purpose.